

schedule 30 for Plain-End Pipe
 (Data from ASME B36.10 (incorporating ASTM A53 Table 2.2))

DN	NPS	Outside Diameter		Wall Thickness		Plain End Mass		Identification	Schedule No.
		mm	in	mm	in	kg/m	lb/ft		
6	1/8	10.3	0.405	1.45	0.057	0.32	0.21		30
8	1/4	13.7	0.540	1.85	0.073	0.54	0.36		30
10	3/8	17.1	0.675	1.85	0.073	0.70	0.47		30
15	1/2	21.3	0.840	2.41	0.095	1.12	0.76		30
20	3/4	26.7	1.050	2.41	0.095	1.44	0.97		30
25	1	33.4	1.315	2.9	0.114	2.18	1.46		30
32	1 1/4	42.2	1.660	2.97	0.117	2.87	1.93		30
40	1 1/2	48.3	1.900	3.18	0.125	3.53	2.37		30
50	2	60.3	2.375	3.18	0.125	4.48	3.01		30
65	2 1/2	73.0	2.875	4.78	0.188	8.04	5.40		30
80	3	88.9	3.500	4.78	0.188	9.92	6.66		30
90	3 1/2	101.6	4.000	4.78	0.188	11.41	7.66		30
100	4	114.3	4.500	4.78	0.188	12.91	8.67		30
200	8	219.1	8.625	7.04	0.277	36.82	24.72		30
250	10	273.0	10.750	7.8	0.307	51.01	34.27		30
300	12	323.8	12.750	8.38	0.330	65.19	43.81		30
350	14	355.6	14.000	9.53	0.375	81.33	54.62	STD	30
400	16	406.4	16.000	9.53	0.375	93.27	62.64	STD	30
450	18	457	18.000	11.13	0.438	122.38	82.23		30
500	20	508	20.000	12.7	0.500	155.13	104.23	XS	30
550	22	559	22.000	12.7	0.500	171.10	114.92	XS	30
600	24	610	24.000	14.27	0.562	209.65	140.81		30
700	28	711	28.000	15.88	0.625	272.23	182.90		30
750	30	762	30.000	15.88	0.625	292.20	196.26		30
800	32	813	32.000	15.88	0.625	312.17	209.62		30
850	34	864	34.000	15.88	0.625	332.14	222.99		30
900	36	914	36.000	15.88	0.625	351.73	236.35		30

schedule 30 for Threaded and Coupled pipe
 (Data from ASTM A53 Table 2.3)

DN	NPS	Outside Diameter		Wall Thickness		Plain End Mass		Identification	Schedule No.
		mm	in	mm	in	kg/m	lb/ft		
200	8	219.1	8.625	7.04	0.277	38.07	25.53		30
250	10	273	10.75	7.8	0.307	53.27	35.33		30
300	12	323.8	12.75	8.38	0.33	67.72	45.47		30